

Rolls

FLOODED DEEP CYCLE BATTERIES

6 CS 21P

6 VOLTS



CONTAINER: (INNER)	Polypropylene
COVER: (INNER)	Polypropylene - heat sealed to inner container
CONTAINER: (OUTER)	High Density Polyethylene
COVER: (OUTER)	High Density Polyethylene snap fit to outer container
TERMINALS:	Flag with stainless steel nuts & bolts
HANDLES:	Molded

WEIGHT DRY:	98 kg	217 Lbs.
WEIGHT WET:	123 kg	271 Lbs.
LENGTH:	559 mm	22 Inches
WIDTH:	248 mm	9 3/4 Inches
HEIGHT:	464 mm	18 1/4 Inches

PLATE HEIGHT:	273 mm	10.750 Inches
PLATE WIDTH:	143 mm	5.625 Inches
THICKNESS (POSITIVE):	6.60 mm	0.260 Inches
THICKNESS (NEGATIVE):	4.57 mm	0.180 Inches
POSITIVE PLATE DOUBLE WRAPPED WITH SLYVER ENVELOPED WITH HEAVY DUTY SEPARATOR		



CELLS:	21 Plates/Cell	3 Cell
SEPARATOR THICKNESS:	3 mm	0.105 Inches
GLASS MAT INSULATION:	1 mm	0.020 Inches
ELECTROLYTE RESERVE: ABOVE PLATES	95 mm	3.75 Inches

COLD CRANK AMPS (CCA):	0°F / -17.8°C	1764
MARINE CRANK AMPS (MCA):	32°F / 0°C	2175
RESERVE CAPACITY (RC @ 25A):		1353 Minutes

CAPACITY **683 AH**


HOURLY RATE:	SPECIFIC GRAVITY	CAPACITY / AMP HOUR	CURRENT / AMPS
@ 100 HOUR RATE	1.280	963	9.63
@ 72 HOUR RATE	1.280	908	12.62
@ 50 HOUR RATE	1.280	840	16.80
@ 24 HOUR RATE	1.280	710	29.60
@ 20 HOUR RATE	1.280	683	34.15
@ 15 HOUR RATE	1.280	635	42.35
@ 12 HOUR RATE	1.280	594	49.52
@ 10 HOUR RATE	1.280	567	56.69
@ 8 HOUR RATE	1.280	533	66.59
@ 6 HOUR RATE	1.280	485	80.82
@ 5 HOUR RATE	1.280	458	91.52
@ 4 HOUR RATE	1.280	423	105.87
@ 3 HOUR RATE	1.280	382	127.49
@ 2 HOUR RATE	1.280	328	163.92
@ 1 HOUR RATE	1.280	232	232.22

Amphere Hour capacity ratings based on specific gravities of 1.280. Reduce capacities 5% for 1.265 specific gravity and 10% for specific gravities of 1.250


WWW.ROLLSBATTERY.COM

SPEC 01

CYCLE LIFE VS. DEPTH OF DISCHARGE



VOLTAGE VS. DEPTH OF DISCHARGE



SURRETTE BATTERY COMPANY 1 STATION RD SPRINGHILL, NS CANADA B0M 1X0

1/1/2014 REV. 1