

Rolls

FLOODED DEEP CYCLE BATTERIES

6 CS 25P

6 VOLTS



CONTAINER: (INNER)	Polypropylene
COVER: (INNER)	Polypropylene - heat sealed to inner container
CONTAINER: (OUTER)	High Density Polyethylene
COVER: (OUTER)	High Density Polyethylene snap fit to outer container
TERMINALS:	Flag with stainless steel nuts & bolts
HANDLES:	Molded

WEIGHT DRY:	115 kg	254 Lbs.
WEIGHT WET:	144 kg	318 Lbs.
LENGTH:	559 mm	22 Inches
WIDTH:	286 mm	11 1/4 Inches
HEIGHT:	464 mm	18 1/4 Inches

PLATE HEIGHT:	273 mm	10.750 Inches
PLATE WIDTH:	143 mm	5.625 Inches
THICKNESS (POSITIVE):	6.60 mm	0.260 Inches
THICKNESS (NEGATIVE):	4.57 mm	0.180 Inches
POSITIVE PLATE DOUBLE WRAPPED WITH SLYVER ENVELOPED WITH HEAVY DUTY SEPARATOR		



CELLS:	25 Plates/Cell	3 Cell
SEPARATOR THICKNESS:	3 mm	0.105 Inches
GLASS MAT INSULATION:	1 mm	0.020 Inches
ELECTROLYTE RESERVE: ABOVE PLATES	95 mm	3.75 Inches

COLD CRANK AMPS (CCA):	0°F / -17.8°C	2184
MARINE CRANK AMPS (MCA):	32°F / 0°C	2610
RESERVE CAPACITY (RC @ 25A):		1624 Minutes

CAPACITY **820 AH**


HOURLY RATE:	SPECIFIC GRAVITY	CAPACITY / AMP HOUR	CURRENT / AMPS
@ 100 HOUR RATE	1.280	1156	11.56
@ 72 HOUR RATE	1.280	1091	15.15
@ 50 HOUR RATE	1.280	1009	20.17
@ 24 HOUR RATE	1.280	853	35.53
@ 20 HOUR RATE	1.280	820	41.00
@ 15 HOUR RATE	1.280	763	50.84
@ 12 HOUR RATE	1.280	713	59.45
@ 10 HOUR RATE	1.280	681	68.06
@ 8 HOUR RATE	1.280	640	79.95
@ 6 HOUR RATE	1.280	582	97.03
@ 5 HOUR RATE	1.280	549	109.88
@ 4 HOUR RATE	1.280	508	127.10
@ 3 HOUR RATE	1.280	459	153.07
@ 2 HOUR RATE	1.280	394	196.80
@ 1 HOUR RATE	1.280	279	278.80

Amphère Hour capacity ratings based on specific gravities of 1.280. Reduce capacities 5% for 1.265 specific gravity and 10% for specific gravities of 1.250


WWW.ROLLSBATTERY.COM

SPEC 01

CYCLE LIFE VS. DEPTH OF DISCHARGE



VOLTAGE VS. DEPTH OF DISCHARGE



SURRETTE BATTERY COMPANY 1 STATION RD SPRINGHILL, NS CANADA B0M 1X0

1/1/2014 REV. 1